


Product name	RIKAVINYTHER S60		
Chemical name	Alkyl(C16-18) vinyl ether		
M.W.	Mixture	Structural formula of RIKAVINYTHER S60	
ENCS No	2-372		
CAS RN [®]	822-28-6/930-02-9		
EINECS No	212-495-2/213-208-3		
TSCA	Listed/Listed		

Feature/Function	<p>RIKAVINYTHER (Alkyl vinyl ether) can be imparted the properties of plasticity, water resistance by copolymerizing with monomers of vinyl chloride, vinylidene chloride, vinyl acetate, acrylonitrile, maleate ester.</p> <p>It is used for adhesives, paints, and lubricants.</p> <p>RIKAVINYTHER S60 is a mixture of cetyl vinyl ether, stearyl vinyl ether, etc.</p>
Applications	Adhesives, paints, lubricants

<Representative properties>			
Color (Hazen)	≤80	Freezing point(°C)	17-22
Specific gravity (30/4°C)	0.814-0.824	Flash point(°C)	168
Refractive index (30°C)	1.430-1.440	Boiling point(°C)	140-200/0.4 kPa

Packing	Drum(170kg)
---------	-------------

For inquiries, contact us:	New Japan Chemical co., Ltd. Polymer Materials Marketing & Sales Dept. +81-3-5540-8106
----------------------------	--

<About handling of the descriptions herein>

Descriptions herein were created based on materials, information, and data that have been obtained to date, but the data, evaluations, risks, etc. described are not warranted at all. In addition, the items described are intended for usual ways of handling, and therefore if the product is handled in a special manner, handle it after taking a safety measure appropriate for the application or usage.

